

TABELLA CORRISPONDENZE AISI/EN

Numero acciaio		Designazione alfa-numerica	Famiglia
AISI	EN 10088	EN 10088	
302	1.4310	X 10 CrNi 18-8	AUSTENITICI
303	1.4305	X 8 CrNiS 18-9	
303 Cu	1.4570	X 6 CrNiCuS 18-9-2	
304	1.4301	X 5 CrNi 18-10	
304L 2	1.4306	X 2 CrNi 19-11	
304L	1.4307	X 2 CrNi 18-9	
304 Cu	1.4567	X 3 CrNiCu 18-9-4	
309	1.4828	X 15 CrNiSi 20-12	
310	1.4845	X 8 CrNi 25-21	
316	1.4401	X 5 CrNiMo 17-12-2	
316 L	1.4404	X 2 CrNiMo 17-12-2	
316L Mo	1.4435	X 2 CrNiMo 18-14-3	
316 Mo	1.4436	X 3 CrNiMo 17-13-3	
316 Ti	1.4571	X 6 CrNiMoTi 17-12-2	

(316L Cu)	1.4578	X 3 CrNiCuMo 17-11-3-2	

317	(1.4449)	(X 3 CrNiMo 18-12-3)	
317L	1.4438	X 2 CrNiMo 18-15-4	
317L N	1.4439	X 2 CrNiMoN 17-13-5	
321	1.4541	X 6 CrNiTi 18-10	
329	1.4460	X 3 CrNiMoN 27-5-2	DUPLEX
347	1.4550	X 6 CrNiNb 18-10	AUSTENITICO
409	1.4512	X 2 CrTi 12	FERRITICI
(409 Cb)	1.4601	(X 6 CrNb 12)	
410	1.4006	X 12 Cr 13	MARTENSITICI
416	1.4005	X 12 CrS 13	
420	1.4028	X 30 Cr 13	
(420F)	1.4029	X 29 CrS 13	
420C	1.4034	X 46 Cr 13	
(420F 3)	1.4035	X 46 CrS 13	
420A	1.4021	X 20 Cr 13	
430	1.4016	X 6 Cr 17	FERRITICI
430F	1.4105	X 6 CrMoS 17	
430L Nb	1.4511	X 3 CrNb 17	
431	1.4057	X 17 CrNi 16-2	MARTENSITICO
434	1.4113	X 6 CrMo 17-1	FERRITICI

436	1.4513	X 2 CrMoTi 17-1	MARTENSITICI
439	1.4510	X 3 CrTi 17	
440B	1.4112	X 90 CrMo V 18	
440C	1.4125	X 35 CrMo 17	
441	1.4509	X 2 CrTiNb 17	FERRITICI
444	1.4521	X 2 CrMoTi 18-2	PH
446	1.4762	X 10 CrAlSi 25	
630	1.4542	X 5 CrNiCuNb 16-4	
631	1.4568	X 7 CrNiAl 17-7	
904L	1.4539	X 1NiCrMoCu 25-20-5	AUSTENITICO
NESSUNA CORRISPONDENZA	1.4104	X 14 CrMoS 17	MARTENSITICI
	1.4122	X 39 CrMo 17-1	DUPLEX
	1.4362	X 2 CrNi 23-4	
	1.4410	X 2 CrNiMo 25-7-4	
	1.4418	X 4 CrNiMo 16-5-1	MARTENSITICO
	1.4462	X 2 CrNiN 22-5-3	DUPLEX
	1.4501	X 2 CrNiMoCuWN 25-7-4	
	1.4507	X 2 CrNiMoCuN 25-6-3	