

TOLLERANZE TOLERANCES

Larghezza Width

Spessore nominale in mm Nominal thickness in mm		Tolleranze normali in mm per una larghezza nominale Tolerances on the thickness for a nominal width in mm				
da / from	a / to	≤125	>125 a ≤250	>250 a ≤600	>600 a ≤1000	>1000 a ≤2100
÷	≤ 2,0	± 1,0	± 1,0	± 1,2	± 2,0	± 2,5
> 2,0	≤ 3,0	± 1,2	± 1,2	± 1,5	± 3,0	± 3,0
> 3,0	≤ 6,0	± 2,0	± 2,0	± 2,0	± 3,5	± 4,0
> 2,5	≤ 10,0	± 2,0	± 3,0	± 3,5	± 4,0	± 5,0
> 10,0	≤ 15,0	± 2,5	± 3,0	± 4,0	± 5,0	± 6,0

Planarità Planarity

Spessore nominale in mm Nominal thickness in mm		Larghezza nominale in mm Nominal width in mm		Tolleranze sulla planarità Tolerances on planarity	
da / from	a / to	da / from	a / to	Normali	Speciali
> 2,0	≤ 25		≤ 1200	15 mm	8 mm
> 2,0	≤ 25	> 1200	≤ 1500	18 mm	9 mm
> 2,0	≤ 25	> 1500		23 mm	12 mm

Spessore Thickness

Spessore in mm Thickness in mm		Tolleranze sullo spessore per una larghezza nominale in mm Tolerances on the thickness for a nominal width in mm			
da - from	a - to	≤1200	>1200 a ≤1500	>1500 a ≤1800	> a 1800
÷	≤ 2,0	± 0,17	± 0,19	± 0,21	÷
> 2,0	≤ 2,5	± 0,18	± 0,21	± 0,23	± 0,25
> 2,5	≤ 3,0	± 0,20	± 0,22	± 0,24	± 0,26
> 3,0	≤ 4,0	± 0,22	± 0,24	± 0,26	± 0,28
> 4,0	≤ 5,0	± 0,24	± 0,26	± 0,28	± 0,29
> 5,0	≤ 6,0	± 0,26	± 0,28	± 0,29	± 0,31
> 6,0	≤ 8,0	± 0,29	± 0,30	± 0,31	± 0,35
> 8,0	≤ 10,0	± 0,32	± 0,33	± 0,34	± 0,40
> 10,0	≤ 12,5	± 0,35	± 0,36	± 0,37	± 0,43
> 12,5	≤ 15	± 0,37	± 0,38	± 0,40	± 0,46
> 15,0	≤ 25	± 0,40	± 0,42	± 0,45	± 0,50

Lunghezza Length

Lunghezza in mm Length in mm		Tolleranze in mm Tolerances in mm
da / from	a / to	
÷	2000	-0/+30
2000	8000	-0/+30